

GB/T 10044 EZNi-1

AWS A5.15 ENi-CI

EN ISO 1071 E C Ni-CI 3

AK ENi-CI

Description: A nickel-cored electrode designed to weld average grades cast irons .The weld metal is soft and easily machinable; deposition is performed on cold or slightly preheated material. It is suitable for joining cast irons to rectify casting and repair broken parts.

Application: Used to thin weld parts of cast irons and repair broken parts.

Typical Chemical Composition(%):

	C	Si	Mn	S	P	Ni	Fe	Al	Cu
Requirement	2.0	2.5	1.0	0.030	—	≥85	8.0	1.0	2.5
Actual Result	0.23	0.97	0.16	0.004	0.024	97.2	1.1	0.24	0.003

Recommended welding parameters:

Diameter/mm		2.5	3.2	4.0
Welding current/A	F/H	70- 110	100- 140	140- 180
	V/ OH	—	—	—